

VM-100500

2309 Industrial Drive
P.O. Box 4219
Sidney, Ohio 45365
Phone: 937-492-3100
Fax: 937-492-3108
www.visionmark.com

Transfer Tape with Fiber Reinforced Acrylic Pressure Sensitive Adhesive

Product Description:

- Adhesive Solvent acrylic (5 mils thick)
- Liner 60# silicone coated paper (3.4 mils thick)

Applications:

- Bonds well to a wide variety of substrates including various metals, low surface energy plastics, and foams

Features & Benefits:

- High performance in extreme environments
- A good balance of tack and shear
- Good slitting and converting
- Resistant to solvents and high temperatures
- Excellent resistance to heat, moisture, and various chemicals
- Contact your VisionMark's Customer Service Sales Representative for further information

Environmental Performances:

Service Temperature Range -40°F (-40°C) to 300°F (-34°C to 149°C)
Minimum Application Temperature 40°F (5°C)

Product Data:

<u>PHYSICAL PROPERTIES:</u>	<u>VALUE:</u>
180° Peel to Stainless Steel.....	115 oz/in (15 minute dwell)
Loop Tack to Stainless Steel	78 oz/in
Expected Shear (1" x 1" x 1000g)	200 Hours (no failure)

Disclaimer: The conditions of your use and application of our product, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our product, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by VMI. All information is given without warranty or guarantee. It is expressly understood and agreed that customer assumes and hereby expressly released VMI from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind VMI. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.